

Surface

Species<sup>1</sup> or Product

**PREFINISHED**

**JARRAH**

**82.55mm Cover x 18mm Thick SOLID WOOD  
FLOORING**

**Ready to Lay  
NOTHING MORE TO DO**



**LEXUS  
Spotted Gum  
Showroom  
Sydney**

Hardness Comparison (Janka Test kN)

|                                |                               |                                        |                       |
|--------------------------------|-------------------------------|----------------------------------------|-----------------------|
| Hardness (Janka Test)          | 8.5kN                         | Density                                | 820 kg/m <sup>3</sup> |
| Wide/Cover (mm)                | 82.55                         | Amount per Unit/Box <sup>[4]</sup>     | 1.04 Square Metres    |
| Lengths <sup>[2]</sup> (mm)    | 2100                          | Formaldehyde Emission                  | 'E0'(no emission)     |
| Thickness (mm)                 | 18                            | Coating Gloss Level                    | 35% SATIN             |
| Packed <sup>[4]</sup>          | 6 pieces high x 1 wide        | Coating                                | 7 layers 125g/m2      |
| Grade                          | Recycled/Waste Recovery       | Coating Wear Resistance <sup>[3]</sup> |                       |
| Scientific Name <sup>[1]</sup> | Eucalyptus marginata & others | Moisture Content                       | 6% to 10%             |

Information provided is based on sample test averages and there will be variation from piece to piece.

Suitable for relative humidity from 30% to 60%. See our document "[Moisture Management](#)" for more information.

**FIRE RESISTANCE DATA:** For **critical design** information see our document "[FIRE HAZARD REQUIREMENTS FOR TIMBER FLOORING](#)"

CRITICAL RADIANT FLUX Greater than 4.5kw/m2

Smoke Development Rate less than 750%-min

<sup>[1]</sup> Species of recycled/waste recovery grade may include a range & are identified based on appearance and properties – See our document "[Sources of Wood](#)" for more information.

<sup>[2]</sup> Lengths usually made up to 2100mm. Some combinations of lengths made up to as short as 1800mm are occasionally supplied.

<sup>[3]</sup> Taber Test – See our document "[Floor Life](#)" for more information.

<sup>[4]</sup> Sometimes square metres will vary to utilise all lengths. If you need exactly the indicated square metres please check with us.

The Briggs group – 100 years in timber – 1908 to 2008 ©