

Surface	Species ¹ or Product	
SAWN unseasoned	WESTERN REDGUM	F14, MINIMUM Durability class 2 above ground use



Information provided is based on sample test averages and there will be variation from piece to piece.

Minimum Hardness (Janka)	6kN	Minimum Density	1200 kg/m ³
Lengths	up to 12m	Moisture Content	Unseasoned
Sizes	up to 450 x 450	Formaldehyde Emission	'E0'(no emission)
Packed	Slings approximately 600mm x 600mm	Treatment	untreated
Scientific Names ¹		Minimum Grade	F14 to AS2082

Eucalyptus species including crebra, teretocornis, resinifera, diversicolor, fibrosa, sideroxylon, gummifera, terminalis, longifolia, miniata,

FIRE RESISTANCE DATA: For **critical design** information see our document "[FIRE HAZARD REQUIREMENTS FOR TIMBER FLOORING](#)"
CRITICAL RADIANT FLUX Greater than 4.5kW/m2 Smoke Development Rate less than 750%-min

The Briggs group – 100 years in timber – 1908 to 2008 ©

Information provided is subject to change without notice. Please check with us for the most up to date documents.

12-Mar-09